

# Soudacryl C920 Flex

**strybuc**  
INDUSTRIES  
WINDOW AND DOOR HARDWARE

- Premium Grade Elastomeric Acrylic Latex
- Permanent Color
- Paintable\*
- Mildew Resistant
- UV Resistant
- Easy clean-up with water
- Non-yellowing
- Very Easy Application
- VOC Compliant
- Colors: White, Clear
- Meets: ASTM C920, Type S, Grade NS, Class 25
- Excellent adhesion to:

Wood	Drywall
Masonry	Metal
Brick	Glass
Concrete	

**59-190: Clear**

**59-190W: White**

\*Allow a minimum of 2 hours dry time before painting with latex or oil base paint

**Weather-tight Sealing  
Window & Door Installs  
Kitchen & Bathroom**



This information and all further technical advice are based on SOUDAL present knowledge and experience. However, SOUDAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. SOUDAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SOUDAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SOUDAL reserves the right to make any changes according to technological progress or further developments.

PA: 2006 Elmwood Avenue - Suite 102C • Sharon Hill, PA 19079 • 800-352-0800 • Fax: 610-534-3202

FL: 4181 West 108th Street - Suite 7 • Hialeah, FL 33018 • 800-780-5051 • Fax: 305-557-5239

[www.strybuc.com](http://www.strybuc.com)

# Soudacryl C920 Flex



Base	Acrylic latex	
Sag	No sag in vertical displ. @120°F	ASTM C639
Curing system	Moisture evaporation	
Tooling time (*)	+/- 10 minutes	@ 75°F & 50% relative humidity
Tack-free time (*)	< 1 hour	ASTM C679
% Non-volatile	61% (clear) - 81% colors	
Shrinkage	25%	ASTM C733-87
pH	8.0	
Movement capability	+/- 25%	ASTM C920
Service temperature range	-20°F to +185°F	
Application temperature range	+40°F to +110°F	
Shelf life	12 months	Stored between 41°F & 77°F
VOC	28 g/L	

(\*) These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

## Limitations:

- Soudal recommends a preliminary compatability test, especially on PVD and non-porous materials.
- Not recommended for continuous water immersion.
- Not recommended for vehicular or foot traffic.
- This product is not to be used as a structural glazing sealant.

## CAUTION:

KEEP OUT OF REACH OF CHILDREN. Avoid skin and eye contact. On contact, uncured sealant could cause irritation to skin and eyes. In case of eye contact, flush eyes with warm water for 15 minutes, call a physician. For skin contact, remove sealant with a paper towel. If swallowed, do not induce vomiting, call a physician. Soudaseal C920 is manufactured for professional use only. Refer to Safety Data Sheet (SDS) for further information.

PLEASE REFER TO TECHNICAL DATA SHEET FOR CLOMPLETE INFORMATION ABOUT THE PRODUCT

