

Soudaseal AP-2



59-189: White

- All Purpose – Bonds to concrete, brick, masonry, aluminum, vinyl, wood, glass, fiber cement, Kynar 500® and many more building materials
- +/- 35% movement capabilities
- Paintable in one hour (prior testing required)
- 100% solids – no shrinkage
- UV Stable – No yellowing or degradation
- Isocyanate free – No outgassing – No bubbling
- Fast skin time – Less dirt pick up
- Bonds to damp* surfaces
- Weather resistant plastic cartridge
- Guns the same in hot and cold temperatures
- Colors: 450+ & Custom Colors
- AAMA approved
- Meets ASTM C-920, Type S, Grade NS, Class 35

* Not for constant immersion

** Some colors may be subject to MOQ's and lead times



**Windows & Doors
Roofing & Siding
General Construction
Concrete & Masonry**

This information and all further technical advice are based on SODAL present knowledge and experience. However, SODAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, SODAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SODAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SODAL reserves the right to make any changes according to technological progress or further developments.

PA: 2006 Elmwood Avenue - Suite 102C • Sharon Hill, PA 19079 • 800-352-0800 • Fax: 610-534-3202

FL: 4181 West 108th Street - Suite 7 • Hialeah, FL 33018 • 800-780-5051 • Fax: 305-557-5239

www.strybuc.com

Soudaseal AP-2

SOUDAL

Base	Silyl-terminated polymer	
Sag	No sag in vertical displ. @120°F	ASTM C639
Curing system	Moisture Cure	
Skin Formation (*)	18 minutes	@ 75°F & 50% relative humidity
Tack-free time (*)	60 minutes	ASTM C679
Curing time (*)	36-72 hrs, 1/4" diameter bead	@ 75°F & 50% relative humidity
Hardness - Shore A	25 +/- 5	ASTM C 661
Tensile Yield	250 psi	ASTM D 412
Elongation	800%	ASTM D 412
Movement capability	+/-35%	ASTM C 719
Stain and color change	Passes	ASTM C 510 (mortar)
Artificial weathering	No Cracking	ASTM C 793
Service temperature range	-40°F to +200°F	
Application temperature range	-35°F to +140°F	Pass
Shelf life	12 months	Stored between 41°F & 77°F
VOC	< 2% - < 30 g/L	Directive 2004/42/EG

(*) These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

Limitations:

Pre-testing for adhesion is intended to eliminate potential problems. This testing will aid in determining the proper surface preparation method.

- May be painted, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application. The drying time of alkyd resin based paints may increase.
- Can be applied to a wide variety of substrates. Due to the fact that specific substrates such as plastics, like polycarbonate, etc. may differ from manufacturer to manufacturer, we recommend preliminary compatibility tests.
- Lower temperatures and humidity will extend curing time.
- Contact with plasticizer containing plastics (e.g. flexible PVC, butyl rubber, EPDM, ...) can lead to incompatibilities, such as discoloration or loss of adhesion. We recommend a preliminary compatibility test.
- We recommend a preliminary adhesion test on every surface.

CAUTION:

KEEP OUT OF REACH OF CHILDREN. Avoid skin and eye contact. On contact, uncured sealant could cause irritation to skin and eyes. In case of eye contact, flush eyes with warm water for 15 minutes, call a physician. For skin contact, remove sealant with a paper towel. If swallowed, do not induce vomiting, call a physician. SoudaSeal AP-2 is manufactured for professional use only. Refer to Safety Data Sheet (SDS) for further information.

PLEASE REFER TO TECHNICAL DATA SHEET FOR COMPLETE INFORMATION ABOUT THE PRODUCT

SOUDAL FEATURES

